

Appln. No. 10/620,887

Attorney Docket No. 10541-1858

**I. Listing of Claims**

1. (Currently Amended) A blue glass composition for automotive glazing comprising a soda-lime-silica base and a colorant portion, said colorant portion consisting essentially of:  
  
about 0.4 to 0.65 weight percent total iron oxide in the form of Fe<sub>2</sub>O<sub>3</sub>,  
greater than about 0.1 to about 0.3 weight percent manganese oxide,  
cobalt oxide in an amount to produce a cobalt concentration of about  
0.0002 to 0.0013 weight percent,  
  
wherein the redox ratio is between about 0.43 and 0.58,  
  
said blue glass composition being characterized by between about 68  
to 76 percent Illuminant A transmittance, about 54 to 64 percent ultraviolet  
transmittance, about 12 to 22 percent infrared transmittance, a dominant wavelength  
between about 486 and 490 nanometers, and a purity excitation between about 7  
and 11 percent, as determined at 4.0 mm thickness.
2. (Original) The blue glass composition of claim 1 wherein the base  
comprises:  
  
about 68 to 75 weight percent SiO<sub>2</sub>,  
about 10 to 18 weight percent Na<sub>2</sub>O,  
about 5 to 15 weight percent CaO,  
0 to about 10 weight percent MgO,  
0 to about 5 weight percent Al<sub>2</sub>O<sub>3</sub>; and  
0 to about 5 weight percent K<sub>2</sub>O.

Appln. No. 10/620,887

Attorney Docket No. 10541-1858

3. (Original) The blue glass composition of claim 1 wherein the base is characterized by a total of  $\text{Na}_2\text{O}$  and  $\text{K}_2\text{O}$  between about 10 and 20 weight percent.

4. (Original) The blue glass composition of claim 1 wherein the dominant wavelength is between about 488 and 489 nanometers.

5. (Original) The blue glass composition of claim 1 wherein the total amount of iron oxide is between about 0.45 and 0.55 weight percent.

6. (Original) The blue glass composition of claim 1 wherein the manganese oxide is between about 0.14 and 0.2 weight percent.

7. (Original) The blue glass composition of claim 1 wherein the cobalt concentration due to cobalt oxide is between about 0.0003 and 0.0010 weight percent.

8. (Currently Amended) ~~The A~~ blue glass composition of claim 1 ~~wherein the blue glass composition is for use as automotive or architectural glazing comprising a soda-lime-silica base and a colorant portion, said colorant portion consisting essentially of:~~

about 0.4 to 0.65 weight percent total iron oxide in the form of  $\text{Fe}_2\text{O}_3$ .

greater than about 0.1 to about 0.3 weight percent manganese oxide,

cobalt oxide in an amount to produce a cobalt concentration of about 0.0002 to 0.0013 weight percent,

wherein the redox ratio is between about 0.43 and 0.58.

BRINKS  
HOFFER  
GILSON  
& LIONE

Appln. No. 10/620,887

Attorney Docket No. 10541-1858

said blue glass composition being characterized by between about 68 to 76 percent Illuminant A transmittance, about 54 to 64 percent ultraviolet transmittance, about 12 to 22 percent infrared transmittance, a dominant wavelength between about 486 and 490 nanometers, and a purity excitation between about 7 and 11 percent, as determined at 4.0 mm thickness.

9. (Original) The blue glass composition of claim 1 wherein the blue glass contains between about 0.03 and 0.12 weight percent  $\text{SO}_3$ .

10. (Original) The blue glass composition of claim 1 wherein the blue glass contains between about 0.05 and 0.08 weight percent  $\text{SO}_3$ .

BRINKS  
HOFER  
GILSON  
ELIENE